

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-295087

(43)Date of publication of application : 09.11.1993

(51)Int.Cl.

C08G 59/40
C08G 59/40
C08G 59/18
C08L 63/00
G02F 1/1339
G09F 9/35
// C08G 59/17

(21)Application number : 04-122936

(71)Applicant : KYORITSU KAGAKU SANGYO KK

(22)Date of filing : 17.04.1992

(72)Inventor : FUKUMOTO KUNIHIRO

KOJIMA KAZUYUKI

SHIRAHAMA YOSHIHARU

(54) FRAME SEALING AGENT COMPOSITION FOR LIQUID CRYSTAL DISPLAY

(57)Abstract:

PURPOSE: To provide the subject composition capable of improving the workability in producing simply in a short time high-grade liquid crystal displays.

CONSTITUTION: The objective curable composition essentially comprising (A) at least one kind of partially (meth)acrylated epoxy resin obtained by reaction of a bisphenol A-type epoxy resin with (meth)acrylic acid, (B) (meth)acrylic ester monomer(s) or oligomer (s) thereof, (C) an epoxy resin, (D) a photopolymerization initiator, and (E) a potential epoxy curing agent. The water-soluble ionic substance content of this composition is $\leq 40\mu\text{S}/\text{cm}$ in terms of ionic conductivity.

LEGAL STATUS

[Date of request for examination]

26.02.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3162179

[Date of registration]

23.02.2001

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office